

File 351:Derwent WPI 1987-2001/UD,UM &UP=200142

(c) 2001 Derwent Info Ltd

*File 351: Price changes as of 1/1/01. Please see HELP RATES 351.

72 Updates in 2001. Please see HELP NEWS 351 for details.

Set Items Description

--- -----

?e dx=87-337282

Ref	Items	Index-term
E1	1	*DX=1987-337282
E2	1	DX=1987-337283
E3	1	DX=1987-337284
E4	1	DX=1987-337285
E5	1	DX=1987-337286
E6	1	DX=1987-337287
E7	1	DX=1987-337288
E8	1	DX=1987-337289
E9	1	DX=1987-337290
E10	1	DX=1987-337291
E11	1	DX=1987-337292
E12	1	DX=1987-337293

Enter P or PAGE for more

?s e1

S1 1 DX="1987-337282"

?t s1/5/all

1/5/1

DIALOG(R)File 351:Derwent WPI

(c) 2001 Derwent Info Ltd. All rts. reserv.

007340276

WPI Acc No: 1987-337282 /198748

XRAM Acc No: C87-143961

Purple coloured sintered alloy for ornament - contains intermetallic cpd. comprising gold, aluminium, and also at least one of nickel, cobalt and palladium

Patent Assignee: SEIKO DENSHI KOGYO KK (DASE)

Number of Countries: 001 Number of Patents: 002

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 62240729	A	19871021	JP 8683026	A	19860410	198748 B
JP 89007143	B	19890207				198909

Priority Applications (No Type Date): JP 8683026 A 19860410

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
JP 62240729	A		2		

Abstract (Basic): JP 62240729 A

Alloy contains intermetallic cpd. comprising 70-83wt.% Au, and 30-17wt.% Al, as a main component, and 7-30wt.% at least one of Ni, Co and Pd.

USE - The sintered alloy has attractive purple colour, 75-105 kg/mm2 deflective strength, and hardness of 240-310 Hv, further equivalent corrosion resistance to conventional Au alloy.

0/0

Title Terms: PURPLE; COLOUR; SINTER; ALLOY; ORNAMENT; CONTAIN;
INTERMETALLIC; COMPOUND; COMPRISE; GOLD; ALUMINIUM; ONE; NICKEL; COBALT;
PALLADIUM

Derwent Class: M22; M26

International Patent Class (Additional): C22C-001/04; C22C-005/02

File Segment: CPI